

Ir polish: Removal rates (Å/min):

Abrasive (2 wt%) Chemical (0.1 mol/l Kg final slurry solution); Raw chem. amount in "grams"

Raw Chemical				Slurry abrasive			
Formula	FW	Abs. wt%	0.1mol/lKg	CR1	CR6	CR30	CR85

H5IO6	228	5	22.8	286	233	288	116
H5IO6+TMAH to pH6-7						325	